

HUNENG INTERNATIONAL TRADE CO.,LTD



ADD:ROOM 140A HENG TONG OFFICE BUILDING,NO.56 BEIJING ROAD,QINGDAO FREE TRADE ZONE,QINGDAO,CHINA

Tel: 86 532 84461850 Fax: 86 532 84461859

performance parameters ---insulating glass

Structure		Light Properties		Thermal Properties			U Value
Insulating Glass	Thickness	LT (%)	LR (%)	EA (%)	SHGC (%)	SC	W/M ² ·K (air)
Low-e	4-12-4mm	74	17	26	65	0.75	1.9
	5-12-5mm	73	17	28	64	0.74	1.9
	6-12-6mm	73	16	31	63	0.73	1.9
	8-12-8mm	71	16	36	60	0.7	1.9
	10-12-10mm	70	16	40	58	0.67	1.9