



HUNENG INTERNATIONAL TRADE CO.,LTD

ADD:ROOM 140A HENG TONG OFFICE BUILDING,NO.56 BEIJING ROAD,QINGDAO
FREE TRADE ZONE,QINGDAO,CHINA

Tel: 86 532 84461850 Fax: 86 532 84461859

performance parameters ---mirror

Items		Quality Requirements	
		Mirror Quality (MQ)	Select Quality (SQ)
Thickness Tolerance (mm)	Thickness (mm)	Tolerance	Tolerance
	2	1.80-2.20	1.80-2.20
	3	2.70-3.00	2.70-3.00
	4	3.80-4.20	3.80-4.20
	5	4.70-5.00	4.70-5.00
	6	5.80-6.20	5.80-6.20
	8	6.70-7.00	7.70-8.30
	10	7.70-8.00	9.70-10.30
	12	8.70-9.00	11.70-12.30
Size Tolerance (mm)	Thickness (mm)	Stock Inventory Sheets	Cut Size
	2.0-6.0	±3mm	±2mm
	8.0-12.0	±6mm	±3mm
Bow & Dish (mm)	2.0-3.0	$\leq 1.5\text{mm/m}$	
	4.0-12.0	$\leq 1.5\text{mm/m}$	
Edge Quality (mm)	Flake	$\leq 4\text{mm}$	
	Bevel/Flare	$\leq 3\text{mm}$	
	Corner On/Off	$\leq 4\text{mm}$	
Over Score & Cutter Drag		Not allowed	Not allowed
Squareness	For all thickness	Diagonal measurement difference/2 $\leq 0.2\%$ the diagonal length	
Optical Distortion	2.0-3.0mm	Zebra $\geq 50^\circ$	
	4.0-12.0mm	Zebra $\geq 55^\circ$	
Surface Flaws	Linear Flaws	When viewed under a normal fluorescent inspection light source	
		Not visible viewed at 0.5meter	Not visible viewed at 1 mter
	Spot Marks	Same as for linear flaws	Same as for linear flaws
Point Defects	Defect Size (d)	Number of defects allowed per square meter of glass	
	$d \leq 0.5\text{mm}$	Allowed	
	$0.5 < d \leq 1.0\text{mm}$	0.3	Allowed
	$0.5 < d \leq 1.5\text{mm}$	0.1	0.2
	$d \geq 1.5\text{mm}$	None	