



HUNENG INTERNATIONAL TRADE CO.,LTD

ADD:ROOM 140A HENGTONG OFFICE BUILDING,NO.56 BEIJING ROAD,QINGDAO FREE TRADE ZONE,QINGDAO,CHINA

Tel: 86 532 84461850 Fax: 86 532 84461859

performance parameters ---reflective glass

Colors	Thickness (mm)	Visible Light Transmittance (%)	Visible Light Reflectance (%)	UV Light Transmittance (%)	Direct Sunlight Transmittance (%)	Direct Sunlight Reflectance (%)	Total Solar Transmittance (%)	Shadowing Coffecient (SC)	RHG	K Value (Summer Daytime)	K Value (Winter Night)
Bronze	5	25.78	16.60	2.73	35.79	14.70	47.73	0.54	0.51	5.272	5.843
	6	20.45	16.32	2.03	29.70	14.85	43.08	0.48	0.46	5.243	5.808
Euro Grey	5	24.96	15.82	3.85	32.98	14.02	45.76	0.51	0.49	5.272	5.843
	6	21.26	15.36	3.05	28.01	13.37	42.15	0.47	0.46	5.243	5.808
Dark Grey	5	24.93	17.13	4.68	32.67	15.22	45.24	0.51	0.48	5.272	5.843
	6	20.82	14.09	3.50	27.39	12.71	41.83	0.47	0.46	5.243	5.808
Light Blue	5	28.47	31.89	4.39	30.29	22.01	41.80	0.47	0.45	5.256	5.824
	6	25.33	31.63	3.54	26.14	21.17	38.85	0.44	0.42	5.243	5.808
Dark Blue	5	23.35	13.46	12.07	43.49	18.44	52.68	0.59	0.55	5.272	5.843
	6	18.79	11.79	10.23	38.68	17.19	49.32	0.55	0.52	5.243	5.808
F. Green	5	28.40	35.11	3.13	24.11	19.91	37.61	0.42	0.41	5.272	5.843
	6	26.43	34.12	2.76	20.76	18.66	35.37	0.40	0.39	5.243	5.808
Dark Green	5	27.31	26.52	4.36	28.14	16.63	41.46	0.47	0.45	5.272	5.843
	6	25.40	24.35	4.06	26.15	15.15	40.30	0.45	0.44	5.243	5.808
Clear	5	50.58	34.10	13.87	58.00	25.85	61.89	0.70	0.63	5.272	5.843
	6	42.75	38.11	9.47	52.31	28.29	56.99	0.64	0.58	5.243	5.808